

Carbon-Structure-Steel

China	International		Former Soviet Union		America				Japan			Germany	England		France
GB/T700	ISO 3573	ISO 630	GOST 535	GOST 380	ASTM A283M	ASTM A573M	ASTM A284M	ASTM A709M	JIS G3101	JIS G3131	JIS G3106	DIN EN10025	BS970 Part1	BS EN10025	NF EN10025
Q195	HR2			CT1KP CT1CP CT1PC	Gr. B				SS330 (SS34)	SPHC SPHD			040A10		
Q215A	HR1		CT2KP-2 CT2PC-2 CT2CP-2		Gr. C	Gr. 58			SS330 (SS34)	SPHC		Fe360C	040A12	Fe360C	Fe360C
Q215B			CT2KP-3 CT2PC-3 CT2CP-3		Gr. C	Gr. 58	Gr. C		SS330 (SS34)	SPHC SPHD			040A12		
Q235A		Fe360A	CT3KP-2 CT3PC-2 CT3CP-2		Gr. D				SS400 (SS41)		SM400A (SM41A)	Fe360B Fe360C	080A15	Fe360B Fe360C	Fe360B Fe360C
Q235B		Fe360D	CT3KP-3 CT3PC-3 CT3CP-3		Gr. D				SS400 (SS41)		SM400A (SM41A)	Fe360B Fe360C	080A15	Fe360B Fe360C	Fe360B Fe360C
Q235C		Fe360D	CT3KP-4 CT3PC-4 CT3CP-4		Gr. D	Gr. 65	Gr. D				SS400A (SS41A) SM400B	Fe360C	080A15	Fe360C	Fe360C
Q235D		Fe360D	CT3KP-4 CT3PC-4 CT3CP-4						SS400A (SS41A)			Fe360D1 Fe360D2		Fe360D1 Fe360D2	Fe360D1 Fe360D2
Q255A			CT4KP-2 CT4PC-2 CT4CP-2					Gr. 36[250]	SS400 (SS41)		SS400A (SS41A)				
Q255B			CT4KP-3 CT4PC-3 CT4CP-3					Gr. 36[250]	SS400 (SS41)		SS400A (SS41A)				
Q275		Fe430A	CT5KP-2 CT5CP-2						SS490 (SS50)						