

Hardenability-Alloy-Structure-Steel

Project	China GB, YB	Japan JIS	Germany DIN (W-Nr.)	America			England BS	France NF	Former Soviet Union Г О С Т	International ISO
				ASTM	AISI	SAE				
		SMn433H (SMn1H)		1330H	1330H	1330H				
		SMn438H (SMn2H)		1041H	1041H	1041H				
		SMn443H (SMn3H)		1041H	1041H	1041H				
		SCr420H (SCr22H)		5120H	5120H	5120H				
		SCr430H (SCr2H)		5130H	5130H	5130H	530H30			
		SCr435H (SCr3H)		5135H	5135H	5135H	503H36			
		SCr440H (SCr4H)		5140H	5140H	5140H	503H40			
		SCM418H		4118H	4118H	4118H				
		SCM435H (SCM3H)		4135H	4135H	4135H	640H35	30CD4		
		SCM440H (SCM4H)		4140H	4140H	4140H	708H42			
		SCM445H (SCM5H)		4145H	4145H	4145H				
		SNC631H (SNC2H)						30NC11		
		SNC815H (SNC22H)					655H13			
		SNCM220H (SNCM21H)		8620H	8620H	8620H		20NCD2		
		SNCM420H (SNCM23H)		4320H	4320H	4320H				